

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 63301264  
PUBLICATION DATE : 08-12-88


APPLICATION DATE : 30-05-87  
APPLICATION NUMBER : 62136227

APPLICANT : NITTO ELECTRIC IND CO LTD;

INVENTOR : HAMABUCHI KAZUFUMI;

INT.CL. : C09D 3/58

TITLE : COATING COMPOSITION



ABSTRACT : PURPOSE: To obtain a coating composition which can form a thick film excellent in properties after curing even on a wet surface or underwater in good applicability, by using a curing agent based on a xylylenediamine derivative as a curing agent for a coating composition containing an epoxy resin, a curing agent and a thixotropic agent.

CONSTITUTION: A coating composition containing an epoxy resin, a curing agent and a thixotropic agent, wherein the thixotropic index is 3-20. Said curing agent is based on a combination of a polyamideamine (A) derived from xylylenediamine and an acryl derivative (B) of xylylenediamine. It is desirable that 10-150pts.wt. component B is present per 100pts.wt. component A. Examples of component A include condensation products of xylylenediamine with a dimer or trimer acid, obtained by polymerizing an unsaturated fatty acid such as linoleic acid or oleic acid. Examples of component B include reaction products of xylylenediamine with an acrylic compound having a structure of formula I (wherein X is H or CH<sub>3</sub>).

COPYRIGHT: (C)1988,JPO&Japio

DERWENT-ACC-NO: 1989-027842

DERWENT-WEEK: 198904

COPYRIGHT 2006 DERWENT INFORMATION LTD

TITLE: Paint compsn. using epoxy! resins- contains resin  
thixotropic agent and curing agent contg. polyamidamine  
and acrylic deriv. of xylylidene di:amine

PATENT-ASSIGNEE: NITTO ELECTRIC IND CO[NITL]

PRIORITY-DATA: 1987JP-0136227 (May 30, 1987)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAINIPC
<u>JP 63301264 A</u>	December 8, 1988	N/A	005	N/A

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO	APPL-DATE
JP 63301264A	N/A	1987JP0136227	May 30, 1987

INT-CL (IPC): C09D003/58

ABSTRACTED-PUB-NO: JP 63301264A

BASIC-ABSTRACT:

Paint compsn. contains an epoxy resin, a curing agent and a thixotroping agent. The thixotropic index is 3-20, and the curing agent mainly contains (a) a polyamide-amine derived from a xylylenediamine and (b) an acrylic deriv. of a xylylene-diamine.

The epoxy resin is e.g. bisphenol A diglycidyl ether, bisphenol F diglycidyl ether, etc., having pref. the epoxy equivalent of 140-1000 and an average epoxy number of at least 1.5. (a) is e.g. a condensation reaction prod. of (1) a xylylenediamine and (2) polymerised fatty acids e.g. dimeric acid and trimeric acid, obtd. by polymerisation of the fatty acids having unsatd. bond in the mol. like linoleic acid, oleic acid, etc. (b) is e.g. reaction prods. of xylylenediamine with acrylic cpds. (e.g. methylmethacrylate, ethylmethacrylate, etc.), having the amine value 200-700 and the active hydrogen equivalent 30-100.

USE/ADVANTAGE - This compsn. can be thickly coated, having good workability either on wet material or in water and providing excellent film properties after curing.

CHOSEN-DRAWING: Dwg.0/0

TITLE-TERMS: PAINT COMPOSITION POLYEPOXIDE RESIN CONTAIN RESIN THIXOTROPIC  
AGENT CURE AGENT CONTAIN POLYAMIDE AMINE ACRYLIC DERIVATIVE  
XYLYLIDENE DI AMINE

DERWENT-CLASS: A21 A82 G02

CPI-CODES: A05-A01E4; A08-D01; A08-M06; A12-B01L; G02-A02G;

POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:

Key Serials: 0224 0231 1282 3183 1283 1373 3083 3105 1601 3123 2020 2180 2199  
2284 2285 2296 2299 2566 2654 2718 2792

Multipunch Codes: 014 04 141 155 157 163 199 206 220 221 222 226 231 24& 273  
311 336 339 341 360 400 44& 473 477 512 515 53& 55& 57& 575 596 656 720 724

AN 1989:214845 CAPLUS  
DN 110:214845  
ED Entered STN: 10 Jun 1989  
TI Epoxy resin coating compositions  
IN Shimizu, Masahito; Kawamoto, Norio; Hamabuchi, Kazufumi  
PA Nitto Denko Corp., Japan  
SO Jpn. Kokai Tokkyo Koho, 5 pp.  
CODEN: JKXXAF

DT Patent  
LA Japanese  
IC ICM C09D003-58  
CC 42-9 (Coatings, Inks, and Related Products)  
FAN, CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 63301264	A2	19881208	JP 1987-136227	19870530 <--
PRAI	JP 1987-136227		19870530		

CLASS

PATENT NO.	CLASS	PATENT FAMILY CLASSIFICATION CODES
------------	-------	------------------------------------

JP 63301264	ICM	C09D003-58
	IPCI	C09D0003-58 [ICM,4]

AB The title compns., applicable in a greater thickness on wet surfaces than are conventional compns., comprise epoxy resins, crosslinking agents mainly consisting of polyamideamines derived from xylylenediamine (I) and acrylic derivs. of I, and thixotropic agents, and have thixotropic index 3-20. A composition of bisphenol A-based epoxy resin (epoxy equivalent 190)

100, Ph glycidyl ether 10, polyamideamine (amine value 400; active H equivalent 90) from I and linolenic acid dimer acid 30, I-phenoxyethyl acrylate reaction product (amine value 550; active H equivalent 80) 15, diethylenetriamine-linolenic acid dimer acid reaction product (amine value 310; active H equivalent 125) 10, talc 40, TiO<sub>2</sub> 30, colloidal SiO<sub>2</sub> 4.5, and C 0.5 part were mixed at 30° to give a coating with thixotropic index 5. This coating was applied readily in a 3-mm thickness on a vertically held wet steel sheet and cured at 20° over 7 days to form a film which showed adhesive strength 50 kg/cm<sup>2</sup> and du Pont impact strength 35 cm, while a coating with thixotropic index 1.5 was not applicable in uniform thickness and cured to form a film with adhesive strength 35 kg/cm<sup>2</sup> and du Pont impact strength 30 cm.

ST epoxy coating thixotropic index control; wet surface coating epoxy resin; xylylenediamine deriv curing epoxy coating

IT Thixotropic substances

(epoxy resin coatings containing, applicable on wet surface in thick-layered coat)

IT Coating materials

(epoxy resins, containing xylenediamine derivative curing agents and thixotropic substances, applicable on wet surface in thick-layered coat)

IT Asbestos

RL: USES (Uses)

(thixotropic substances, epoxy resin coatings containing)

IT Crosslinking agents

(xylylenediamine derivs., for epoxy resin coatings)

IT 463-40-1D, Linolenic acid, dimer acid, reaction products with xylylenediamine 26603-36-1D, Xylylenediamine, reaction products with linolenic acid dimer acid 26603-36-1D, Xylylenediamine, reaction products with phenoxyethyl acrylate or lauryl acrylate 48145-04-6D, Phenoxyethyl acrylate, reaction products with xylylenediamine  
RL: MOA (Modifier or additive use); USES (Uses)

(crosslinking agents, epoxy resin coatings containing)

IT 7631-86-9, Silica, uses and miscellaneous 14807-96-6, Talc, uses and miscellaneous

RL: USES (Uses)

Partial English translations Japanese Patent Kokai (Laid-Open)

Patent Laid-Open No. 63-301264

Laid-Open date : December 12, 1988

Request for Examination : None

Patent Application No. 62-136227

Application date : May 30, 1987

Inventor(s) : Hamabuchi Kazufumi et al

Applicant : Nitto Electric Industry Co, Ltd

Title of the invention : Coating composition

(Names of individuals and corporation have been translated phonetically)

Claim 1 : A coating composition comprising an epoxy resin, a curing agent and a thixotropic agent, wherein it has a thixotropic index of 2 to 20 and said curing agent contains a polyamide amine derived from xylylendiamine and an acrylic derivative of xylylenediamine as main components.

(Page 1, lower left col., lines 11 to 16)

3. Detail Description of the Invention


[Field of Industrial Application]

The present invention relates to a coating composition used an epoxy resin. Its object is to develop a coating composition which is capable of coating to a thick film and is excellent in applicability on a wet surface or under water.

(Page 2, upper left col. line 5 to upper right col. line 3)

Examples of the epoxy resin to be used in the present invention include epoxy resins which have been used hitherto.

Examples of such epoxy resin include resins having at least one substituted or non-substituted glycidyl group (e.g., glycidylether, glycidylester, glycidylamine, glycidylimine, etc) per molecule represented by the following formula



wherein Z shows a hydrogen atom, a methyl group or an ethyl group.

In more detail, examples of such epoxy resin include diglycidylether of bisphenol A, diglycidylether of bisphenol F, an epoxy resin of phenol novolac and diglycidylether of alkylene oxide adduct of bisphenols.


(Page 2, lower left col. lines 2 to 13)

The curing agent to be used in the present invention contains two components of a polyamide amine derived xylylenediamine and an acrylic derivative of xylylenediamine as main components.

- 1 4 Examples of the polyamide amine derived from xylylendiamine include a condensation product of (1) xylylendiamine and (2) a polymerized fatty acids such as a dimer acid or a trimer acid, obtained by polymerized a fatty acid having an unsaturated bond such as linolenic acid, oleic acid, 8 linoleic acid, eladic acid or recinoleic acid.

(Page 2, lower left col. line 19 to lower right col. line 4)

Examples of the acrylic derivative of xylylendiamine include a reaction product of xylylendiamine and an acrylic compound having a structure represent by the following formula:



wherein X shows a hydrogen atom or a methyl group.

(Page 3, upper right col. lines 6 to 16).

In the present invention, it is necessary to use together the above-mentioned two species of curing agent. Even if either one of these species is used, intended advantageous effects cannot be expected.

Intended advantageous effects are exhibited without depending on any blending ratio of these two species, so long as these two species of curing agent are used together. However, from the viewpoint to improve further characteristics of curried coating film to be obtained 10 to 150 parts by weight of the acrylic derivative of xylylendiamine per 100 parts by weight to the polyamide amine derived xylylendiamine is preferable.

(Page 4, upper left col. lines 2 to 19)

(Example)

The present invention is described in more detail below referring to Examples. Hereinafter, the word "part" means "part by weight".

#### Example 1

100 parts of bisphenol A type epoxy resin (epoxy equivalent 190), 10 parts of phenylglycidylether, 30 parts of polyamide amine (amine value 400, active hydrogen equivalent 90) obtained by reaction of xylylendiamine and dimmer acid of linolenic acid, 15 parts of an acrylic

derivative (amine value 550, active hydrogen equivalent 80) obtained by reaction of xylylendiamine and phenoxyethylacrylate, 10 parts of a reaction product (amine value 310, active hydrogen equivalent 125) of diethylenetriamine and dimer acid of linolenic acid, 40 parts of talc, 30 parts of titanium white, 45 parts of colloidal silica and 0.5 parts of carbon were mixed in a stirring mixing vessel, whereby a coating composition having a thixotropic index of 5 was obtained.

⑨ 日本国特許庁(JP)

⑩ 特許出願公開

⑪ 公開特許公報(A)

昭63-301264

⑫ Int. Cl.

C 09 D 3/58

⑬ 特許記号

PJX

⑭ 庁内整理番号

7224-4J

⑮ 公開 昭和63年(1988)12月8日

審査請求 未請求 発明の数 1 (全5頁)

⑯ 発明の名称 塗料組成物

⑰ 特 願 昭62-136227

⑱ 出 願 昭62(1987)5月30日

発 明 者 清水 雅 人 大阪府茨木市下穂積1丁目1番2号 日東電気工業株式会社内

発 明 者 河 本 紀 雄 大阪府茨木市下穂積1丁目1番2号 日東電気工業株式会社内

発 明 者 濱 潤 一 文 大阪府茨木市下穂積1丁目1番2号 日東電気工業株式会社内

⑲ 出 願 人 日 東 電 工 株 式 会 社 大阪府茨木市下穂積1丁目1番2号

特 許 代 理 人 弁 理 士 尾 関 弘

## 明 細 書

## 1. 発明の名称

塗料組成物

## 2. 特許請求の範囲

(1) エポキシ樹脂、硬化剤および顔料を含有して成る塗料組成物であって、そのチクトロビュグインデックスが3〜20であり、且つ硬化剤がキシリレンジアミンより誘導されたポリア(ドアミンおよびキシリレンジアミンのアクリル誘導体を主成分とするものである塗料組成物。

## 3. 発明の詳細な説明

(産業上の利用分野)

本発明は、エポキシ樹脂を用いた塗料組成物に關し、その目的とする所に厚膜に塗布することが出来、且つ塗膜面あるいは水中部に於ける施工性に優れた塗料組成物を提供することである。

(従来技術)

従来から各種の塗料組成物が広い分野で使用されており、そのうちの一種としてエポキシ樹脂を用いた塗料がある。このエポキシ樹脂を用いた

塗料組成物は、エポキシ樹脂本来の有する優れた特性を利用したもので、多くの長所を有するものである。

(発明が解決しようとする問題点)

しかしながら、最近の技術の進歩によりこの種のエポキシ樹脂を使用した塗料組成物についても更に進んだ性能が要求されつつある。特に、施工作業性に優れ、厚膜施工ができ且つ低価格であるいは水中での補修体に対しても優れた施工性をもって作業でき、しかも硬化後の強度力、耐衝撃性等の物性に優れた塗料組成物の開発が強く望まれるようになって来た。

(問題点を解決するための手段)

本発明は上記の要望に応えたものであって、硬化後の特色に優れた厚膜を塗膜面や水中部に於いても施工性よく形成できる塗料組成物を開発することを目的としており、エポキシ樹脂、硬化剤および顔料を含有して成る塗料組成物であって、硬化剤としてキシリレンジアミンより誘導されたポリア(ドアミンおよびキシリレンジアミンのア




## 特開昭63-301264 (2)

クリル誘導体を主成分とするものを使用し、且つ組成物のチクソトロピックインデックスを1〜20とすることによって達成される。

(発明の構成並びに作用)

本発明で用いられるエポキシ樹脂としては、従来からこの種塗料用として使用されてきたエポキシ樹脂を挙げることができる。

かようなエポキシ樹脂として、例えば下記式、



(式中、Zは水素原子、メチル基またはエチル基を示す)

で示される置換または非置換のグリシジル基(例えば、グリシジルエーテル、グリシジルエステル、グリシジルアミン、グリシジルイミン等)を分子内に少なくとも1個有するものを例示することができる。そのようなエポキシ樹脂として、具体的には、ビスフェノールAのジグリシジルエーテル、ビスフェノールFのジグリシジルエーテル、フェ

ノールノボラックのエポキシ樹脂、ビスフェノール類のアルキレンオキッド付加物のジグリシジルエーテル等を挙げることができる。

上記エポキシ樹脂のエポキシ当量は特に制限はないが、好ましくはエポキシ当量140〜1800程度のもので用いられる。エポキシ当量が小さいものは、得られる硬化塗膜の特性が低下し、逆に大きすぎるものは、エポキシ樹脂が固型状となる傾向がある。

また、1分子中の平均エポキシ基が1.5個以上のものを用いるのが好ましく、平均エポキシ基が1.5個以上のものを使用することにより得られる硬化塗膜の特性を向上せしめることが出来る。

本発明で用いるエポキシ樹脂の性状は、通常液状または半固型状のものが使用され、固型のエポキシ樹脂は、α-ブチルグリシジルエーテル、アリルグリシジルエーテル、2-エステルヘキシルグリシジルエーテル、ステレンオキライド、フェニルグリシジルエーテル等固型のエポキシ樹脂を溶剤しうる溶剤類と混合して、液状または半固型状

として用いることができる。

本発明に於いて用いられる硬化剤は、キシレンジアミンより誘導されたポリアミドアミンおよびキシレンジアミンのアクリル誘導体という特定の二成分を主成分とするものである。


キシレンジアミンより誘導されたポリアミドアミンとしては、

(1) キシレンジアミンと、

(2) リノレイン酸、オレイン酸、リノール酸、エライジン酸、リノレイン酸等の分子中に不飽和結合を有する脂肪酸を重合させて得られるダイマー酸、トリマー酸等の重合脂肪酸との割合反応生成物を挙げることができる。

上記のようなポリアミドアミンは通常、アミン価100〜300、活性水素当量50〜150とされる。アミン価、活性水素当量が上記範囲を外れると、得られる硬化塗膜の特性が低下する傾向を示すため好ましくない。

キシレンジアミンのアクリル誘導体としては、例えば、キシレンジアミンと下記式



(式中、Xは水素原子またはメチル基を示す)

で示される構造を有するアクリル系化合物との反応生成物を挙げることができる。

上記アクリル誘導体を製造するための原料として用いられるアクリル系化合物としては、例えばメチルメタクリレート、エチルメタクリレート、n-ブチルメタクリレート、iso-ブチルメタクリレート、2-エステルヘキシルメタクリレート、インデシルメタクリレート、ラウリルメタクリレート、ステアリルメタクリレート、ノタアクリル酸、2-ヒドロキシエチルメタクリレート、2-ヒドロキシプロピルメタクリレート、2-ヒドロキシエチルアクリレート、ジメチルアミノメチルメタクリレート、ジエチルアミノメチルメタクリレート、エチレンジオールメタクリレート、ジエチレンジオールジメタクリレート、トリエチレン

## 特開昭63-301264 (3)

グリコールジメタクリレート、トリメチロールプロペントリメタクリレート、ネオブチルエチルメタクリレート、テトラヒドロフルフリルメタクリレート、テトラヒドロフルフリルアクリレート、グリンジメタクリレート、1,3-ブタンジオールジメタクリレート、モノ(2-メタクリロイロキシエチル)アシッドホスファート、モノ(2-アクリロイロキシエチル)アシッドホスファート、アクリル酸エチルカルビトール、アクリル酸ノルトリグリコール、テトラヒドロフルフリルアクリレート、2-ヒドロキシ-3-フェニルオキシプロピルアクリレート、トリメチロールプロペントリアクリレート、1,6-ヘキサジオールジアクリレート、2-ヒドロキシエチルアクリロイルホスファート、ブトキシエチルアクリレート、ラウリルアクリレート、ステアリルアクリレート、トリエチレンジグリコールジアクリレート、ネオペンテングリコールジアクリレート、フェノール誘導体のアクリレート等を挙げることができる。

アミン、ポリメルカプタン、アミン内塩アジド、アミン分解アジド等を挙げることができる。

上記硬化剤の配合量は、エポキシ樹脂のエポキシ当量100に対して硬化剤全体の活性水素当量0.5～2.5当量とするのが良い。0.5当量に満たない場合は硬化物の硬化が不十分となり、2.5当量を超えると未反応の硬化剤が残存することがある。

本発明の原料組成物には、阻害剤(チクソトロピー性)を加えるために阻害剤を配合し、そのチクソトロピシティンデックスを1～20程度もしくは5～15にする。

上記チクソトロピシティンデックスが3に満たない場合は、未硬化状態の塗膜が重れ、均一な塗膜を得るのが困難となり、また水中にあっては未硬化塗膜が被覆体より剥れ易く、一方20を超えらるものでは塗布時の作業性が低下するとともに得られる硬化塗膜の平滑性が不十分となるため好ましくない。

尚、本発明でいうチクソトロピシティンデックスとは、25℃の条件下、ブルックフィールド固

また、上記の如きアクリル誘導体は通常、アミン当量200～700、活性水素当量20～1000のものが用いられ、上記範囲を外れたものでは、得られる硬化塗膜の特性が低下する傾向が生じ好ましくない。

本発明に於いては、上記の2種類の硬化剤を使用することが必要であり、いずれか1種類では所望の効果を期待することはできない。

そしてこれ等2種類の硬化剤を併用するか否かこれ等2種類の配合割合のいかんにかかわらず所望の効果を奏する。但しこの得られる硬化塗膜の特性をより一層向上させる見地より、キシリレンジアミンより誘導されたポリアミドアミン100重量部に対し、キシリレンジアミンのアクリル誘導体10～150重量部とするのが好ましい。

また、本発明では上記2種の硬化剤に加え、他の硬化剤を10重量%以下の割合で配合して用いることもできる。かような硬化剤としては、脂肪族アミン、脂環族アミン、前記以外のポリアミド

樹脂原料を用いて、1回転で測定した値と10回転で測定した値との比を意味する。

前記の阻害剤の具体例としては、疎水性シリカあるいはアスベスト、ペントナイト、タルク等の粘土鉱物等を挙げることができる。

本発明で用いる上記阻害剤の配合量は、チクソトロピシティンデックスが所定の値となる量配合されることを基本とし、配合する材料の性質等により適宜に決定されれば良いが、通常はエポキシ樹脂100重量部に対して0.1～50重量部程度配合される。

また、本発明では原料組成物の粘度、比重調整、施工性向上あるいは硬化物の機械的強度向上、応力緩和等の目的のために各種充填剤を配合することもできる。かような充填剤としては例えば、炭酸カルシウム、クレー、カーボンブラック、チタン白、硫酸バリウム、金属粉末、ガラス粉末、ガラスフレーク、無機質繊維あるいは、有機質、染料、着色顔料、防錆剤等を挙げることができ、エポキシ樹脂100重量部に対して1～300重

## 特開昭63-301264 (4)

量部相度配合される。

## (実施例)

以下、実施例を示して本発明を具体的に説明する。尚、以下において部は重量部を意味する。

## 実施例1

ビスフェノールA型エポキシ樹脂（エポキシ当量190）100部、フェニルグリシジルエーテル10部、キシレンジアミンとリノレイン酸のダイマー酸との反応により得られたポリアミドアミン（アミン当量400、過性水素当量90）30部、キシレンジアミンとフェノキシエチルアクリレートとの反応により得られたアクリル誘導体（アミン当量550、過性水素当量80）15部、ジエチレントリアミンとリノレイン酸のダイマー酸との反応生成物（アミン当量110、過性水素当量125）10部、タルク40部、チタン白30部、コロイダルシリカ15部およびカーボン0.5部を原料配合量中30で混合して、チクソトロピックインデックス5の塗料組成物を得た。

## 比較例1

## 実施例3

実施例1に於いてポリアミドの配合量を60部とし、ジエチレントリアミンとリノレイン酸のダイマー酸との反応生成物を配合しない他は全て実施例1と同様にして、チクソトロピックインデックス5の塗料組成物を得た。

## 比較例3

実施例1に於いてキシレンジアミンより誘導されたポリアミドアミンおよびキシレンジアミンとフェノキシエチルアクリレートとの反応により得られたアクリル誘導体を用いず、ジエチレントリアミンとリノレイン酸のダイマー酸との反応生成物（前出）の配合量を55部とする他は全て実施例1と同様にして、チクソトロピックインデックス5の塗料組成物を得た。

上記各実施例および比較例で得られた塗料組成物を、垂直に立てられた平滑状態の銅板にハケで塗布した。

実施例1～3の塗料組成物は容易に均一な厚さ（3mm）に塗布することができたが、比較例1の

実施例1に於いて、タルクに代え、炭酸カルシウム70部、コロイダルシリカを全く使用せずその他は全て実施例1と同様にしてチクソトロピックインデックス1.5の塗料組成物を得た。

## 実施例2

実施例1に於いて、ビスフェノールA型エポキシ樹脂に代えビスフェノールF型エポキシ樹脂（エポキシ当量175）100部、タルクの配合量を60部、コロイダルシリカに代え、アスベスト5部とする他は全て実施例1と同様にして、チクソトロピックインデックス1.5の塗料組成物を得た。

## 比較例2

実施例1に於いてフェノキシエチルアクリレートの代わりにチウリルアクリレートを用いたアクリル誘導体（アミン当量550、過性水素当量80）15部、コロイダルシリカに代えアスベスト7部を配合する他は全て実施例1と同様にして、チクソトロピックインデックス2.5の塗料組成物を得た。

塗料組成物はたれやすく3mmの均一な厚さが得られず、比較例2の塗料組成物は非常に乾りにくく、又比較例3の塗料組成物では一部に塗布されない部分が残った。

上記のように銅板上に塗布した塗料組成物を20℃の条件下7日で硬化させ、硬化後の塗膜特性を下記方法により測定した。結果を、後記第1表に示す。

## &lt;塗膜硬さ&gt;

エルコノーク社製のアドヒージョンテスターにより測定した。

## &lt;耐衝撃強度&gt;

デュポン式衝撃試験機にてJIS K 5400に準じ、衝撃径0.5インチ、荷重5kgの条件下第1表に示す高さから荷重を落し、測定した。

○：銅板に達するクラック、われ割

×：銅板に達するクラック、われ有

特開昭63-301264 (6)

図 1 表

	実施例			比較例		
	1	2	3	1	2	3
塗膜粘着力 (kg/cm)	50	45	45	35	10	5
耐衝撃強度	35cm ○	40cm ○	35cm ○	30cm ○	20cm ○	5cm ×

(発明の効果)

上記のように、本発明の塗料組成物は、湿潤面  
水中部にあっても容易に膜厚を形成でき、しかも  
硬化後の塗膜特性が良好である。

(以上)

特許出願人 日東電業工業株式会社

代 理 人 弁 理 士 尾 崎 弘 